

Reorder Numbers:

Prelude Self-Etch Kit	Ref # 90990
Prelude Total-Etch Kit	Ref # 90994
Prelude Primer/Adhesive 2/pk 5ml ea	Ref # 91024
Prelude Primer 5ml	Ref # 90972
Prelude Adhesive 5ml	Ref # 90974
Prelude Dual/Self-Cure Link 5ml	Ref # 90976
MicroPrime G Desensitizer 10ml	Ref # 90814
MicroPrime B Desensitizer 10ml	Ref # 87001
SureEtch Gel 5gm	Ref # 89463
50 Micron Aluminum Oxide 1 lb.	Ref # 15301
S-Bond 10ml	Ref # 89104
Z-Bond 5ml bottle	Ref # 93410

- **Store <85°F** and out of sunlight. Refrigeration may extend shelf life.
- **Caution:** Unpolymerized monomers may cause skin irritation. Wash thoroughly with soap and water in case of contact.



3420 Fostoria Way Suite A-200 San Ramon, California 94583 USA
800/827-7940 Fax 925/973-0764

94030 Rev A

Reorder Numbers:

Prelude Self-Etch Kit	Ref # 90990
Prelude Total-Etch Kit	Ref # 90994
Prelude Primer/Adhesive 2/pk 5ml ea	Ref # 91024
Prelude Primer 5ml	Ref # 90972
Prelude Adhesive 5ml	Ref # 90974
Prelude Dual/Self-Cure Link 5ml	Ref # 90976
MicroPrime G Desensitizer 10ml	Ref # 90814
MicroPrime B Desensitizer 10ml	Ref # 87001
SureEtch Gel 5gm	Ref # 89463
50 Micron Aluminum Oxide 1 lb.	Ref # 15301
S-Bond 10ml	Ref # 89104
Z-Bond 5ml bottle	Ref # 93410

- **Store <85°F** and out of sunlight. Refrigeration may extend shelf life.
- **Caution:** Unpolymerized monomers may cause skin irritation. Wash thoroughly with soap and water in case of contact.



3420 Fostoria Way Suite A-200 San Ramon, California 94583 USA
800/827-7940 Fax 925/973-0764

94030 Rev A



Prelude is a nanohybrid, light cured, self-etch or total-etch dental adhesive ideal for bonding to dentin, enamel, prepared canals, porcelain, composite, and metals. Its low film thickness of 5 microns does not interfere with the fit of indirect restorations.

- Compatible with all composites, compomers and resin cements.
- **MicroPrime G applied to etched or primed enamel and dentin surfaces prior to Adhesive** application provides desensitization without diminishing the bond. Prelude in self-etch mode normally does not have sensitivity issues, however it still benefits from MicroPrime G's antimicrobial action.
- **Never mix Prelude components;** use sequentially, drying in between applications.
- **Adhesive Endodontic:** place materials onto prepared canal walls with appropriate endodontic brushes. Do not use paper points.
- **Eugenol** will inhibit set. Sure Etch will remove residual eugenol.
- **Avoid saliva and blood contamination.**
- **Shake Adhesive bottle well prior to first use** to redisperse fillers after extended storage.
- **Adhesion to self-cure or dual-cure** cements requires Prelude Dual/Self-Cure Link. When Prelude Adhesive and Dual/Self-Cure Link are used with cements, Prelude will polymerize without light, making it self-cure.




Prelude is a nanohybrid, light cured, self-etch or total-etch dental adhesive ideal for bonding to dentin, enamel, prepared canals, porcelain, composite, and metals. Its low film thickness of 5 microns does not interfere with the fit of indirect restorations.


- Compatible with all composites, compomers and resin cements.
- **MicroPrime G applied to etched or primed enamel and dentin surfaces prior to Adhesive** application provides desensitization without diminishing the bond. Prelude in self-etch mode normally does not have sensitivity issues, however it still benefits from MicroPrime G's antimicrobial action.
- **Never mix Prelude components;** use sequentially, drying in between applications.
- **Adhesive Endodontic:** place materials onto prepared canal walls with appropriate endodontic brushes. Do not use paper points.
- **Eugenol** will inhibit set. Sure Etch will remove residual eugenol.
- **Avoid saliva and blood contamination.**
- **Shake Adhesive bottle well prior to first use** to redisperse fillers after extended storage.
- **Adhesion to self-cure or dual-cure** cements requires Prelude Dual/Self-Cure Link. When Prelude Adhesive and Dual/Self-Cure Link are used with cements, Prelude will polymerize without light, making it self-cure.

Total-Etch:

1 Etch tooth surface for 10 sec with phosphoric acid etchant. **Do not scrub. Rinse well. See below for preparation of other bonding surfaces.**




2 **Do not blow dry. Blot excess water** with a new MicroBrush®, foam pellet or large paper point.




- Continue at Step 3. (on next page)

OR:**Self-Etch (no etchant required)**

1 Apply Primer to damp or dry enamel and dentin. **Scrub for 10 sec** with a MicroBrush®. Do not rinse.



2 Use an air syringe to gently **evaporate the solvent**. Surface need not remain shiny.



- Continue at Step 3. (on next page)

Preparation of Other Surfaces:

First, air abrade all bonding surfaces of restorations being cemented or repaired using Danville's MicroEtcher and 50 micron Aluminum Oxide.

Next, follow instruction related to surface type: Composites, Porcelain and Lithium Disilicate - Apply S-Bond according to its instructions and continue at Step 3 on next page.


Zirconia, Alumina, and Metals - Apply Z-Bond according to its instructions. Surface is ready for composite or cement.

Amalgam - Begin at Self-Etch Step 1, above.


Precious and Non-Precious Metals - Begin at Step 3 on next page. Tin-Plating of precious metal bonding surfaces improves bond strength.

Adhesive Application (Follow steps 1 and 2 on previous page and continue at step 3 below.):


3 Apply Adhesive with a new MicroBrush®. **Scrub for 10 sec.**



4 **Evaporate solvent** with gentle air stream. Increase air pressure to **thin Adhesive**.



5 **Light Cure 10 sec.** Light cure is optional when using Dual/Self-Cure Link with self-cure and dual-cure composites.





For direct restorations: Place composite (flowable preferred) or compomer restorative and light cure.

For indirect restorations: See "Preparation of Other Surfaces" on previous page. Follow instructions below for using Dual/Self-Cure Link on every surface where Adhesive has been applied.


Dual/Self-Cure Link for bonding self-cure and dual-cure composites and resin cement.

- Dab Link liberally onto cured or uncured Adhesive with a MicroBrush.® Do not scrub.
- Evaporate solvent with air syringe.
- Apply self-cure or dual-cure composite.
- Initiator in self/dual-cured composites will cause Prelude to become dual-cure.


Warning: Dual/Self-Cure Link may shorten the working time of some self-cure and dual-cure composites.

**Total-Etch:**

1 Etch tooth surface for 10 sec with phosphoric acid etchant. **Do not scrub. Rinse well. See below for preparation of other bonding surfaces.**




2 **Do not blow dry. Blot excess water** with a new MicroBrush®, foam pellet or large paper point.




- Continue at Step 3. (on next page)

OR:**Self-Etch (no etchant required)**

1 Apply Primer to damp or dry enamel and dentin. **Scrub for 10 sec** with a MicroBrush®. Do not rinse.



2 Use an air syringe to gently **evaporate the solvent**. Surface need not remain shiny.



- Continue at Step 3. (on next page)

Preparation of Other Surfaces:

First, air abrade all bonding surfaces of restorations being cemented or repaired using Danville's MicroEtcher and 50 micron Aluminum Oxide.

Next, follow instruction related to surface type: Composites, Porcelain and Lithium Disilicate - Apply S-Bond according to its instructions and continue at Step 3 on next page.


Zirconia, Alumina, and Metals - Apply Z-Bond according to its instructions. Surface is ready for composite or cement.

Amalgam - Begin at Self-Etch Step 1, above.


Precious and Non-Precious Metals - Begin at Step 3 on next page. Tin-Plating of precious metal bonding surfaces improves bond strength.

Adhesive Application (Follow steps 1 and 2 on previous page and continue at step 3 below.):


3 Apply Adhesive with a new MicroBrush®. **Scrub for 10 sec.**



4 **Evaporate solvent** with gentle air stream. Increase air pressure to **thin Adhesive**.



5 **Light Cure 10 sec.** Light cure is optional when using Dual/Self-Cure Link with self-cure and dual-cure composites.



For direct restorations: Place composite (flowable preferred) or compomer restorative and light cure.

For indirect restorations: See "Preparation of Other Surfaces" on previous page. Follow instructions below for using Dual/Self-Cure Link on every surface where Adhesive has been applied.

Dual/Self-Cure Link for bonding self-cure and dual-cure composites and resin cement.

- Dab Link liberally onto cured or uncured Adhesive with a MicroBrush.® Do not scrub.
- Evaporate solvent with air syringe.
- Apply self-cure or dual-cure composite.
- Initiator in self/dual-cured composites will cause Prelude to become dual-cure.

Warning: Dual/Self-Cure Link may shorten the working time of some self-cure and dual-cure composites.

